



**AI TECHNOLOGY INC**  
 70 Washington Road  
 Princeton Jct., NJ 08550  
 (609) 799-9388 fax (609) 799-9308  
 E-Mail: [ait@aitechnology.com](mailto:ait@aitechnology.com)  
 Internet: <http://www.aitechnology.com>

**TACK FILM**  
**TK7758**

**Stress Free, Very High  
 Thermal Conductivity  
 Reworkable  
 Epoxy Film Adhesive**

**IDEAL FOR:**

- Large Area Die Attach
- Substrate and Component
- Reworkability
- Mismatched CTE's

**DESCRIPTION:**

Tack-film TK7758 is a reworkable, aluminum nitride-filled, electrically insulating epoxy film adhesive. It is designed for bonding die, component and substrate to a mismatched substrate or carrier. This B-Staged conductive adhesive offers excellent reworkability at 80-150°C and is storable at -40°C for one year.

TK7758 has excellent thermal conductivity. Its low Tg adhesive imposes minimum thermal stress on bonded parts during thermal cycling or shock testing.

**AVAILABILITY:**

TK7758 is available in sheet sizes or as custom preforms. Standard thicknesses are 0.003" and 0.006". Special thicknesses are available.

**APPLICATION PROCEDURES:**

- ( 1 ) Let adhesive thaw in bag or plastic box, as received, at ambient for 15 minutes.
- ( 2 ) Cut to desired size. Clean contact surfaces if needed.
- ( 3 ) Remove one side of the release paper by peeling up a corner of the release paper. Fold the release paper over, approaching a 180° angle.
- ( 4 ) Pull the release paper quickly, removing it with one stroke. Apply to substrate, then remove other side of release paper and attach die or component.
- ( 5 ) Cure using to one of the recommended schedules.

**TYPICAL PROPERTIES\***

Electrical Resistivity ( 150 °C/ 30 minut )	>1x10 <sup>14</sup> ohm-cm
Dielectric Strength (Volts/mil)	>750
Glass Transition Temp.(°C)	-25
Lap-Shear Strength	1000 psi 6.9 N/mm <sup>2</sup>
Device Push-off Strength	2400 psi 16.6 N/mm <sup>2</sup>
Hardness (Type)	82 (A)
Cured Density (gm/cc)	2.3
Thermal Conductivity	25 Btu-in/hr-ft <sup>2</sup> -°F 3.6 W/m-°C
Linear Thermal Expansion Coeff. (ppm/°C)	110
Maximum Continuous Operation Temp. (°C)	150

\* Properties given are typical values and not intended for use in preparing specifications. The user is advised to evaluate the product in the manner the product is intended to be used in manufacturing and in the final product.

**CURE SCHEDULES:**

Temperature	Time	Pressure
80°C	8 hr	3-5 psi
100°C	4 hr	3-5 psi
125°C	2 hr	3-5 psi
150°C	30 min	3-5 psi
200°C	10 min	3-5 psi
300°C	10 sec	3-5 psi

The die or component can also be tacked on the substrate at 80°C or higher with 5 psi. When a fillet around the edge of the die or component is observed, the pressure can be released for the rest of the bonding cycle.

**SHELF LIFE:**

Storage temperature	Shelf Life
-40°C	1 yr
0°C	6 mo

**CAUTION:** This product may cause skin irritation. Avoid skin contact. If contact does occur, wash immediately with soap and water. Please refer to MSDS for more details.

The information contained herein is believed to be reliable. All recommendations or suggestions are made without guarantee inasmuch as conditions and methods of commercial use are beyond our control. Properties given are typical values and not intended for use in preparing specifications. The user is advised to evaluate the product in the manner the product is to be used in manufacturing and in the final product. Under no circumstance shall A.I. Technology be liable for accidental, consequential or other damages arising from the use or handling of this product.

While AI Technology owns all proprietary rights of material formulations of its products, specific usage in the manufacturing of certain products may involve patent rights of other companies.