



AI TECHNOLOGY INC
 70 Washington Road
 Princeton Jct., NJ 08550
 (609) 799-9388 fax (609) 799-9308
 E-Mail: ait@aitechnology.com
 Internet: <http://www.aitechnology.com>

Flexible Die-Attach
ME8456-DA

Flexible

Stress Free

Low Temperature Curable

Electrically Conductive

Epoxy Paste Adhesive

IDEAL FOR:

Large Area Die

Substrate and Component

Reworkability

Mismatched CTE's

DESCRIPTION:

ME8456-DA is a flexible, pure silver filled, electrically and thermally conductive epoxy paste adhesive for die-attach application. It exhibits outstanding flexibility for bonding materials with highly mismatched CTE's (i.e., alumina to aluminum, silicon to copper). It has been proven to work well for ultra-large area die on ceramic, copper or aluminum substrate.

Die attach with a large area on aluminum have been proven to withstand thermal cycling and shocks from -65 to 150°C for over 1000 times without loss of thermal or mechanical properties. Moisture sensitivity has been improved even for the worst testing conditions. The bond strength recovers its full bond strength after the testing is finished and moisture returns to normal level.

AVAILABILITY:

ME8456-DA is available in syringes for automatic needle dispense applications or in jars. Pot-life is one week at 25°C.

APPLICATION PROCEDURES:

- (1) Thaw for 30 minutes before opening jar.
- (2) Dispense adhesive onto clean substrate.
- (3) Pre-Bake Dispensed Adhesive at 80°C for 30 minutes to achieve optimum bonding. Pre-Bake is not needed in all applications.
- (4) Cure according to one of the recommended schedules.

TYPICAL PROPERTIES*

Electrical Resistivity (150 °C/ 60 min)	<4x10 ⁻⁴ ohm-cm
Dielectric Strength (Volts/mil)	N/A
Glass Transition Temp.(°C)	-20
Current Carrying Capabilities	35 Amp/mm ²
Lap-Shear Strength	1000 psi 6.9 N/mm ²
Device Push-off Strength	>2000 psi >13.8 N/mm ²
Hardness (Type)	80 (A)
Cured Density (gm/cc)	3.5
Thermal Conductivity	>55 Btu-in/hr-ft ² -°F >7.9 W/m-°C
Linear Thermal Expansion Coeff. (ppm/°C)	100
Maximum Continuous Operation Temp. (°C)	150
Avg. Viscosity (5.0 rpm, 24°C) (Brookfield DV-1,spindle CP51)	20,000 cp

* Properties given are typical values and not intended for use in preparing specifications. The user is advised to evaluate the product in the manner the product is intended to be used in manufacturing and in the final product.

CURE SCHEDULES:

<u>Temperature</u>	<u>Time</u>
80°C	8 hr
100°C	4 hr
125°C	2 hr
150°C	1 hr

** For higher temperature curing above 125°C, and/or bonding area of over 1x1 sq cm, it is recommended the dispensed adhesive be pre-baked, open-faced without parts, at 60°C for 30 minutes before parts are mounted and cured.

SHELF LIFE:

<u>Storage temperature</u>	<u>Shelf Life</u>
-40°C	1 yr

The information contained herein is believed to be reliable. All recommendations or suggestions are made without guarantee inasmuch as conditions and methods of commercial use are beyond our control. Properties given are typical values and not intended for use in preparing specifications. The user is advised to evaluate the product in the manner the product is to be used in manufacturing and in the final product. Under no circumstance shall A.I. Technology be liable for accidental, consequential or other damages arising from the use or handling of this product.

While AI Technology owns all proprietary rights of material formulations of its products, specific usage in the manufacturing of certain products may involve patent rights of other companies.