



**AI TECHNOLOGY INC**  
 70 Washington Road  
 Princeton Jct., NJ 08550  
 (609) 799-9388 fax (609) 799-9308  
 E-Mail: ait@aitechnology.com  
 Internet: http://www.aitechnology.com

**PRIMA-BOND  
 ME7630-RC**

**High Strength  
 RAPID CURING  
 Solvent-Free  
 Insulating  
 Epoxy Paste Adhesive**

**IDEAL FOR:**

- Snap Curing
- Smart Card Die Attach
- Automated Assembly

**DESCRIPTION:**

ME7630-RC is a RAPID CURING insulating epoxy adhesive for snap-curing applications. This thixotropic paste is solvent free. (TI is approx. 4.0). It is designed for automated, inline bonding processing.

ME7630-RC is low in ionic impurities (<80 ppm total) and meets all requirements for MIL-Std 883D 5011.4 specification for dielectric adhesive. Fast curing can be achieved from 80°C and higher temperatures.

**AVAILABILITY:**

ME7630-RC is available in syringes for automatic needle dispense applications or in jars.

**APPLICATION PROCEDURES:**

- ( 1 ) Thaw for 30 minutes before opening jar or using syringes.
- ( 2 ) Dispense adhesive onto clean substrate with a suitable pattern to assure full die coverage.
- ( 3 ) Cure according to one of the recommended schedules.

**TYPICAL PROPERTIES\***

Electrical Resistivity ( 150 °C/ 2 min )	>1x10 <sup>14</sup> ohm-cm
Dielectric Strength (Volts/mil)	>750
Glass Transition Temp.(°C)	80
Current Carrying Capabilities	
Lap-Shear Strength	>1500 psi >10.3 N/mm <sup>2</sup>
Device Push-off Strength	>1600 psi >11.0 N/mm <sup>2</sup>
Hardness (Type)	80 ( D )
Cured Density (gm/cc)	1.2
Thermal Conductivity	1.4 Btu-in/hr-ft <sup>2</sup> -°F 0.20 W/m-°C
Linear Thermal Expansion Coeff. (ppm/°C)	40
Maximum Continuous Operation Temp. (°C)	150
Avg. Viscosity(5 rpm, 24°C) (Brookfield DV-1,spindle CP51	8,000 cp

\* Properties given are typical values and not intended for use in preparing specifications. The user is advised to evaluate the product in the manner the product is intended to be used in manufacturing and in the final product.

**CURE SCHEDULES:**

Temperature	Time
80°C	60 min
125°C	15 min
150°C	8 min

**SHELF LIFE:**

Storage temperature	Shelf Life
-40°C	1 yr
25°C	3 mo

The information contained herein is believed to be reliable. All recommendations or suggestions are made without guarantee inasmuch as conditions and methods of commercial use are beyond our control. Properties given are typical values and not intended for use in preparing specifications. The user is advised to evaluate the product in the manner the product is to be used in manufacturing and in the final product. Under no circumstance shall A.I. Technology be liable for accidental, consequential or other damages arising from the use or handling of this product.

While AI Technology owns all proprietary rights of material formulations of its products, specific usage in the manufacturing of certain products may involve patent rights of other companies.