

AI TECHNOLOGY INC 70 Washington Road

Princeton Jct., NJ 08550 (609) 799-9388 fax (609) 799-9308 F-Mail: ait@aitechnology.com

E-Mail: ait@aitechnology.com Internet: http://www.aitechnology.com

Stress Free
100% Solid
Reworkable
Electrically Conductive
Epoxy Paste Adhesive

IDEAL FOR:

Large Area Die Automated Assembly

Reworkability
Mismatched CTE's

DESCRIPTION:

ME8155 is a silver filled paste, reworkable, solvent free, and electrically and thermally conductive. It exhibits outstanding flexibility for bonding materials having highly mismatched CTE's (i.e., alumina to aluminum, silicon to copper).

This paste can be used for screen printing and it can be readily reworked at 80-100°C.

AVAILABILITY:

ME8155 is available in syringes for automatic needle dispense applications or in jars.

APPLICATION PROCEDURES:

- (1) Thaw for 30 minutes before opening jar.
- (2) Dispense adhesive onto clean substrate.
- (3) Cure according to one of the recommended schedules.

PRIMA-SOLDER ME8155

TYPICAL PROPERTIES*

Electrical Resistivity <4x10⁻⁴ ohm-cm (150 °C/ 60 minute)

Dielectric Strength (Volts/mil)

Glass Transition Temp.(°C)

Current Carrying Capabilities

35 Amp/mm²

Lap-Shear Strength >1000 psi

>6.9 N/mm²

Device Push-off Strength >2000 psi

>13.8 N/mm²

Hardness (Type) 80 (A) $\pm 10\%$ Cured Density (gm/cc) 3.5 $\pm 10\%$

Thermal Conductivity 55 Btu-in/hr-ft²-°F ±10%

7.9 W/m-°C ±10%

Linear Thermal Expansion 120 ±15%

Coeff. (ppm/°C)

Maximum Continuous Operation Temp. (°C) <150

Avg. Viscosity(0.5 rpm, 25°C) 354,000 cp ±20%

(Brookfield DV-1,spindle CP51)

CURE SCHEDULES:

Tempe	<u>erature</u>	<u>Time</u>	<u>Presure</u>
	80°C	8 hr	
	100°C	4 hr	
	125°C	2 hr	
	150°C	1 hr	
	175°C	30 min	

SHELF LIFE:

Storage temperature	Shelf Life
-40°C	1 yr
0°C	3 mo

CAUTION: This product may cause skin irritation. Avoid skin contact. If contact does occur, wash immediately with soap and water. Please refer SDS for more details

The information contained herein is believed to be reliable. All recommendations or suggestions are made without guarantee inasmuch as conditions and methods of commercial use are beyond our control. Properties given are typical values and not intended for use in preparing specifications. The user is advised to evaluate the product in the manner the product is to be used in manufacturing and in the final product. Under no circumstance shall Al Technology be liable for accidental, consequential or other damages arising from the use or handling of this product.

While AI Technology owns all proprietary rights of material formulations of its products, specific usage in the manufacturing of certain products may involve patent rights of other companies.

PRODUCT DATA SHEET Ver 2.0 4/2/2018

^{*} Properties given are typical values and not intended for use in preparing specifications. The user is advised to evaluate the product in the manner the product is intended to be used in manufacturing and in the final product.